


A07_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A07_03_PRECRUSH\A07_03_PRECRUSH072.rdf
 Task file: C:\CamsizerXT\CAMSYS\A07_03_PRECRUSH.afg
 Time: 7/21/2015, 10:01, duration 12 min 3 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 495778, CCD-Z = 4916
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		10.8	100.0	0.777	0.907	0.752	27
#20	#16	2.5	89.2	0.731	0.877	0.690	32
#30	#20	2.0	86.7	0.771	0.885	0.691	70
#40	#30	2.2	84.7	0.795	0.867	0.716	255
#50	#40	6.7	82.5	0.850	0.872	0.749	2566
#60	#50	13.3	75.8	0.901	0.893	0.762	9778
#70	#60	17.4	62.5	0.912	0.900	0.747	20075
#140	#70	36.5	45.1	0.899	0.900	0.723	139031
PAN	#140	8.6	8.6	0.850	0.916	0.686	912944



Characteristics

Q3 [%]	x [μm]
10.0	110.9
50.0	222.2
90.0	1262.1
SPAN3 =	5.180
U3 =	2.201
Mv3(x) =	429.8 μm
Sigma3(x) =	577.3 μm

Mean value SPHT3 = 0.867
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.721
 Mean value RDNS_C3 = 0.456
 Mean value SPHT_K3 = 0.647

User