


A09_01_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A09_01_6K\A09_01_6K052.rdf
 Task file: C:\CamsizerXT\CAMSYS\A09_01_6K.afg
 Time: 7/31/2015 , 14:37 , duration 34 min 23 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 122148279 , CCD-Z = 949688
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.796	0.882	0.763	2
#30	#20	0.0	100.0	0.717	0.887	0.745	3
#40	#30	0.0	100.0	0.829	0.899	0.739	17
#50	#40	0.1	100.0	0.756	0.811	0.706	197
#60	#50	1.0	99.9	0.895	0.885	0.784	10786
#70	#60	12.8	98.9	0.928	0.909	0.783	206745
#140	#70	72.6	86.1	0.918	0.909	0.750	3421574
PAN	#140	13.5	13.5	0.864	0.898	0.701	218300574



Characteristics

Q3 [%]	x [μm]
10.0	88.1
50.0	167.5
90.0	218.4
SPAN3 =	0.778
U3 =	2.037
Mv3(x) =	159.5 μm
Sigma3(x) =	53.2 μm

Mean value SPHT3 = 0.906
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.734
 Mean value RDNS_C3 = 0.532
 Mean value SPHT_K3 = 0.670

User