


A10_01_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A10_01_5K\A10_01_5K183.rdf
 Task file: C:\CamsizerXT\CAMSYS\A10_01_5K.afg
 Time: 8/3/2015, 14:11, duration 21 min 7 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 56653158, CCD-Z = 671308
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.882	0.885	0.698	3
#40	#30	0.0	100.0	0.655	0.708	0.728	131
#50	#40	16.4	100.0	0.908	0.898	0.777	191772
#60	#50	41.5	83.6	0.915	0.906	0.751	778726
#70	#60	26.7	42.1	0.911	0.909	0.719	734196
#140	#70	12.3	15.4	0.886	0.900	0.682	862174
PAN	#140	3.1	3.1	0.841	0.900	0.674	145611037



Characteristics

Q3 [%]	x [μm]
10.0	193.4
50.0	258.2
90.0	312.9
SPAN3 = 0.463	
U3 = 1.390	
Mv3(x) = 252.6 μm	
Sigma3(x) = 56.3 μm	

Mean value SPHT3 = 0.901
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.721
 Mean value RDNS_C3 = 0.604
 Mean value SPHT_K3 = 0.639

User