


A10_01_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A10_01_6K\A10_01_6K052.rdf
 Task file: C:\CamsizerXT\CAMSYS\A10_01_6K.afg
 Time: 8/3/2015 , 10:57 , duration 23 min 2 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 93176035 , CCD-Z = 1139125
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.701	0.756	0.747	87
#50	#40	12.7	100.0	0.911	0.900	0.784	118999
#60	#50	37.9	87.3	0.917	0.907	0.759	569024
#70	#60	27.1	49.4	0.914	0.909	0.728	597302
#140	#70	15.8	22.3	0.890	0.899	0.695	968106
PAN	#140	6.5	6.5	0.852	0.901	0.686	204847061



Characteristics

Q3 [%]	x [μm]
10.0	148.9
50.0	250.7
90.0	306.1
SPAN3 = 0.627	
U3 = 1.756	
Mv3(x) = 238.9 μm	
Sigma3(x) = 66.1 μm	

Mean value SPHT3 = 0.901
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.596
 Mean value SPHT_K3 = 0.648

User