


A10_02_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A10_02_CRUSH5K\A10_02_CRUSH5K074.rdf
 Task file: C:\CamsizerXT\CAMSYS\A10_02_CRUSH5K.afg
 Time: 8/11/2015, 15:11, duration 22 min 3 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 65236259, CCD-Z = 808298
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.645	0.696	0.722	2
#40	#30	1.6	100.0	0.890	0.891	0.786	4023
#50	#40	23.5	98.4	0.904	0.899	0.766	141247
#60	#50	29.1	74.9	0.909	0.903	0.754	333793
#70	#60	21.8	45.8	0.909	0.905	0.731	377305
#140	#70	18.6	24.0	0.890	0.899	0.700	880180
PAN	#140	5.4	5.4	0.851	0.899	0.686	100015343



Mean value SPHT3 = 0.896
 Mean value Symm3 = 0.900
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.581
 Mean value SPHT_K3 = 0.651

User