


A10_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A10_02_PRECRUSH\A10_02_PRECRUSH058.rdf
 Task file: C:\CamsizerXT\CAMSYS\A10_02_PRECRUSH.afg
 Time: 7/16/2015, 17:24, duration 13 min 40 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 2797206, CCD-Z = 41994
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.4	100.0	0.733	0.854	0.761	34
#30	#20	2.0	99.6	0.759	0.851	0.740	494
#40	#30	7.2	97.6	0.813	0.858	0.737	4803
#50	#40	23.0	90.4	0.870	0.879	0.738	42254
#60	#50	22.0	67.4	0.897	0.895	0.736	81045
#70	#60	20.2	45.4	0.908	0.903	0.729	118261
#140	#70	24.6	25.2	0.902	0.905	0.708	324993
PAN	#140	0.6	0.6	0.833	0.903	0.667	7260050



Mean value SPHT3 = 0.877
 Mean value Symm3 = 0.890
 Mean value b/l3 = 0.712
 Mean value RDNS_C3 = 0.503
 Mean value SPHT_K3 = 0.627

User