


A10_03_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A10_03_5K\A10_03_5K085.rdf
 Task file: C:\CamsizerXT\CAMSYS\A10_03_5K.afg
 Time: 7/23/2015, 9:53, duration 21 min 11 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 29592471, CCD-Z = 83236
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.720	0.815	0.760	5
#40	#30	1.7	100.0	0.865	0.870	0.778	6026
#50	#40	44.0	98.3	0.907	0.902	0.763	375575
#60	#50	38.0	54.3	0.909	0.908	0.728	527841
#70	#60	8.8	16.3	0.889	0.904	0.674	177673
#140	#70	5.2	7.5	0.863	0.888	0.676	368443
PAN	#140	2.3	2.3	0.763	0.870	0.611	55180673



Characteristics

Q3 [%]	x [μm]
10.0	228.8
50.0	295.4
90.0	362.7
SPAN3 = 0.453	
U3 = 1.339	
Mv3(x) = 292.3 μm	
Sigma3(x) = 65.0 μm	

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.602
 Mean value SPHT_K3 = 0.640

User