


A10_03_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A10_03_6K\A10_03_6K084.rdf
 Task file: C:\CamsizerXT\CAMSYS\A10_03_6K.afg
 Time: 7/22/2015, 14:40, duration 17 min 59 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 32791244, CCD-Z = 99957
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.436	0.649	0.652	3
#40	#30	1.6	100.0	0.862	0.869	0.775	5694
#50	#40	43.4	98.4	0.907	0.901	0.763	370684
#60	#50	38.1	55.0	0.908	0.907	0.728	528267
#70	#60	8.9	16.9	0.889	0.903	0.675	180948
#140	#70	5.6	8.0	0.862	0.888	0.676	384463
PAN	#140	2.4	2.4	0.772	0.874	0.617	65171732



Characteristics

Q3 [%]	x [μm]
10.0	226.1
50.0	294.6
90.0	360.7
SPAN3 =	0.457
U3 =	1.352
Mv3(x) =	290.7 μm
Sigma3(x) =	65.5 μm

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.900
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.598
 Mean value SPHT_K3 = 0.639

User