


A10_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A10_03_PRECRUSH\A10_03_PRECRUSH298.rdf
 Task file: C:\CamsizerXT\CAMSYS\A10_03_PRECRUSH.afg
 Time: 7/15/2015, 15:20, duration 13 min 16 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 7070752, CCD-Z = 111683
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.803	0.854	0.746	4
#20	#16	0.2	99.9	0.711	0.847	0.722	77
#30	#20	1.6	99.7	0.753	0.836	0.730	1133
#40	#30	9.6	98.1	0.830	0.856	0.740	19738
#50	#40	50.4	88.5	0.896	0.897	0.742	262011
#60	#50	22.6	38.1	0.901	0.906	0.712	221038
#70	#60	8.2	15.5	0.898	0.905	0.696	125552
#140	#70	6.4	7.3	0.889	0.901	0.695	295971
PAN	#140	0.9	0.9	0.848	0.911	0.679	18916472



Characteristics

Q3 [%]	x [μm]
10.0	227.9
50.0	320.8
90.0	435.5
SPAN3 = 0.647	
U3 = 1.487	
Mv3(x) = 330.4 μm	
Sigma3(x) = 103.2 μm	

Mean value SPHT3 = 0.880
 Mean value Symm3 = 0.893
 Mean value b/l3 = 0.711
 Mean value RDNS_C3 = 0.575
 Mean value SPHT_K3 = 0.623

User