


A11_02_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A11_02_5K\A11_02_5K083.rdf
 Task file: C:\CamsizerXT\CAMSYS\A11_02_5K.afg
 Time: 7/22/2015, 13:55, duration 32 min 45 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 37089122, CCD-Z = 152887
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.681	0.794	0.670	17
#60	#50	0.1	100.0	0.848	0.856	0.781	947
#70	#60	1.8	99.9	0.902	0.888	0.783	17683
#140	#70	73.8	98.1	0.902	0.900	0.746	3252057
PAN	#140	24.3	24.3	0.854	0.900	0.681	38548921



Characteristics

Q3 [%]	x [μm]
10.0	85.8
50.0	126.5
90.0	176.5
SPAN3 =	0.716
U3 =	1.563
Mv3(x) =	128.5 μm
Sigma3(x) =	36.9 μm

Mean value SPHT3 = 0.885
 Mean value Symm3 = 0.898
 Mean value b/l3 = 0.718
 Mean value RDNS_C3 = 0.499
 Mean value SPHT_K3 = 0.635

User