


## A11\_02\_6K

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDAT\A11\_02\_6K\A11\_02\_6K081.rdf  
 Task file: C:\CamsizerXT\CAMSYS\A11\_02\_6K.afg  
 Time: 7/22/2015, 11:48, duration 33 min 39 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 45688741, CCD-Z = 205478  
 Velocity adaption: no  
 Fitting: no

Material:

| ASTM(+) | No(-) | retained [%] | passing [%] | SPHT3 | Symm3 | b/l3  | PDN      |
|---------|-------|--------------|-------------|-------|-------|-------|----------|
| > #16   |       | 0.0          | 100.0       |       |       |       | 0        |
| #20     | #16   | 0.0          | 100.0       |       |       |       | 0        |
| #30     | #20   | 0.0          | 100.0       |       |       |       | 0        |
| #40     | #30   | 0.0          | 100.0       |       |       |       | 0        |
| #50     | #40   | 0.0          | 100.0       | 0.686 | 0.750 | 0.709 | 10       |
| #60     | #50   | 0.2          | 100.0       | 0.878 | 0.873 | 0.788 | 854      |
| #70     | #60   | 1.9          | 99.8        | 0.914 | 0.895 | 0.786 | 16761    |
| #140    | #70   | 70.7         | 97.9        | 0.906 | 0.903 | 0.748 | 2684076  |
| PAN     | #140  | 27.2         | 27.2        | 0.856 | 0.901 | 0.684 | 80287299 |



## Characteristics

| Q3 [%]              | x [μm] |
|---------------------|--------|
| 10.0                | 77.0   |
| 50.0                | 125.6  |
| 90.0                | 177.8  |
| SPAN3 = 0.802       |        |
| U3 = 1.732          |        |
| Mv3(x) = 126.2 μm   |        |
| Sigma3(x) = 40.3 μm |        |

Mean value SPHT3 = 0.887  
 Mean value Symm3 = 0.901  
 Mean value b/l3 = 0.718  
 Mean value RDNS\_C3 = 0.528  
 Mean value SPHT\_K3 = 0.634

User