


A11_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A11_02_PRECRUSH\A11_02_PRECRUSH304.rdf
 Task file: C:\CamsizerXT\CAMSYS\A11_02_PRECRUSH.afg
 Time: 7/15/2015, 16:57, duration 14 min 51 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 7820332, CCD-Z = 100069
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.8	100.0	0.746	0.884	0.787	25
#20	#16	0.7	99.2	0.768	0.893	0.759	61
#30	#20	1.2	98.5	0.782	0.882	0.739	287
#40	#30	1.8	97.3	0.808	0.880	0.746	1148
#50	#40	2.7	95.5	0.835	0.878	0.749	5275
#60	#50	2.1	92.8	0.849	0.873	0.747	8508
#70	#60	3.5	90.7	0.878	0.880	0.756	24201
#140	#70	58.0	87.2	0.898	0.900	0.740	1839671
PAN	#140	29.2	29.2	0.885	0.924	0.718	11904541



Characteristics

Q3 [%]	x [μm]
10.0	82.3
50.0	127.0
90.0	239.4
SPAN3 = 1.237	
U3 = 1.684	
Mv3(x) = 167.0 μm	
Sigma3(x) = 163.4 μm	

Mean value SPHT3 = 0.880
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.719
 Mean value RDNS_C3 = 0.618
 Mean value SPHT_K3 = 0.633

User