


A12_01_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A12_01_5K\A12_01_5K038.rdf
 Task file: C:\CamsizerXT\CAMSYS\A12_01_5K.afg
 Time: 7/29/2015, 12:51, duration 36 min 11 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 5627980, CCD-Z = 35076
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.645	0.727	0.708	8
#60	#50	0.5	100.0	0.882	0.877	0.781	615
#70	#60	5.1	99.5	0.918	0.899	0.780	10505
#140	#70	79.9	94.4	0.909	0.905	0.744	605689
PAN	#140	14.5	14.5	0.838	0.901	0.663	10930132



Characteristics

Q3 [%]	x [μm]
10.0	96.8
50.0	142.0
90.0	199.3
SPAN3 =	0.722
U3 =	1.587
Mv3(x) =	144.9 μm
Sigma3(x) =	41.8 μm

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.723
 Mean value RDNS_C3 = 0.541
 Mean value SPHT_K3 = 0.645

User