


A12_01_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A12_01_6K\A12_01_6K036.rdf
 Task file: C:\CamsizerXT\CAMSYS\A12_01_6K.afg
 Time: 7/29/2015, 11:19, duration 32 min 45 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 25466867, CCD-Z = 174216
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.319	0.676	0.808	1
#40	#30	0.0	100.0	0.889	0.936	0.811	3
#50	#40	0.0	100.0	0.711	0.827	0.701	36
#60	#50	0.5	100.0	0.886	0.878	0.784	2164
#70	#60	4.8	99.5	0.921	0.901	0.783	37317
#140	#70	78.4	94.7	0.911	0.906	0.749	2273222
PAN	#140	16.3	16.3	0.846	0.901	0.674	51000866



Characteristics

Q3 [%]	x [μm]
10.0	94.0
50.0	140.3
90.0	198.2
SPAN3 =	0.742
U3 =	1.614
Mv3(x) =	142.9 μm
Sigma3(x) =	42.6 μm

Mean value SPHT3 = 0.895
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.550
 Mean value SPHT_K3 = 0.649

User