


A13_01_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A13_01_5K\A13_01_5K037.rdf
 Task file: C:\CamsizerXT\CAMSYS\A13_01_5K.afg
 Time: 7/29/2015, 11:58, duration 34 min 51 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 24731983, CCD-Z = 160770
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.871	0.893	0.690	1
#30	#20	0.0	100.0	0.754	0.892	0.563	1
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.770	0.822	0.711	17
#60	#50	0.4	100.0	0.891	0.883	0.784	1396
#70	#60	3.6	99.6	0.918	0.901	0.778	19768
#140	#70	68.7	96.0	0.904	0.901	0.746	1667182
PAN	#140	27.3	27.3	0.849	0.899	0.680	43735904



Characteristics

Q3 [%]	x [μm]
10.0	79.2
50.0	126.0
90.0	188.8
SPAN3 = 0.871	
U3 = 1.710	
Mv3(x) = 130.2 μm	
Sigma3(x) = 45.0 μm	

Mean value SPHT3 = 0.884
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.715
 Mean value RDNS_C3 = 0.518
 Mean value SPHT_K3 = 0.628

User