


A13-01_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A13-01_6K\A13-01_6K035.rdf
 Task file: C:\CamsizerXT\CAMSYS\A13-01_6K.afg
 Time: 7/29/2015, 10:40, duration 31 min 26 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 72596762, CCD-Z = 485592
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.760	0.851	0.754	6
#50	#40	0.0	100.0	0.741	0.826	0.748	36
#60	#50	0.4	100.0	0.898	0.887	0.789	2908
#70	#60	3.5	99.6	0.920	0.902	0.779	41500
#140	#70	64.7	96.1	0.906	0.902	0.749	3350905
PAN	#140	31.4	31.4	0.856	0.900	0.689	132947484



Characteristics

Q3 [%]	x [μm]
10.0	71.8
50.0	123.2
90.0	188.0
SPAN3 = 0.943	
U3 = 1.848	
Mv3(x) = 126.5 μm	
Sigma3(x) = 45.1 μm	

Mean value SPHT3 = 0.885
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.716
 Mean value RDNS_C3 = 0.527
 Mean value SPHT_K3 = 0.628

User