


A13_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A13_01_PRECRUSH\A13_01_PRECRUSH053.rdf
 Task file: C:\CamsizerXT\CAMSYS\A13_01_PRECRUSH.afg
 Time: 7/16/2015, 16:16, duration 13 min 20 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 11197272, CCD-Z = 130053
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		13.6	100.0	0.809	0.906	0.757	217
#20	#16	5.0	86.4	0.804	0.902	0.731	214
#30	#20	2.0	81.4	0.811	0.893	0.732	234
#40	#30	1.4	79.4	0.822	0.888	0.733	521
#50	#40	1.8	78.0	0.841	0.881	0.746	1960
#60	#50	2.0	76.2	0.872	0.885	0.755	4928
#70	#60	3.6	74.2	0.891	0.889	0.753	14185
#140	#70	39.8	70.6	0.895	0.896	0.736	733957
PAN	#140	30.8	30.8	0.883	0.918	0.712	18694388



Characteristics

Q3 [%]	x [μm]
10.0	76.9
50.0	134.5
90.0	1305.1
SPAN3 = 9.135	
U3 = 2.114	
Mv3(x) = 373.7 μm	
Sigma3(x) = 486.5 μm	

Mean value SPHT3 = 0.865
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.524
 Mean value SPHT_K3 = 0.638

User