


A13_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A13_02_PRECRUSH\A13_02_PRECRUSH061.rdf
 Task file: C:\CamsizerXT\CAMSYS\A13_02_PRECRUSH.afg
 Time: 7/16/2015, 17:51, duration 13 min 5 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 718056, CCD-Z = 7171
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.1	100.0	0.770	0.862	0.785	2
#30	#20	0.3	99.9	0.773	0.843	0.753	18
#40	#30	2.4	99.6	0.805	0.856	0.737	312
#50	#40	14.4	97.2	0.881	0.887	0.753	5265
#60	#50	18.0	82.8	0.902	0.898	0.745	12478
#70	#60	17.1	64.8	0.905	0.900	0.729	18513
#140	#70	37.2	47.7	0.896	0.899	0.719	146785
PAN	#140	10.5	10.5	0.860	0.914	0.686	1330124



Characteristics

Q3 [%]	x [μm]
10.0	104.5
50.0	216.9
90.0	335.0
SPAN3 = 1.063	
U3 = 2.288	
Mv3(x) = 221.6 μm	
Sigma3(x) = 95.2 μm	

Mean value SPHT3 = 0.884
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.713
 Mean value RDNS_C3 = 0.567
 Mean value SPHT_K3 = 0.624

User