


A13_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A13_03_PRECRUSH\A13_03_PRECRUSH319.rdf
 Task file: C:\CamsizerXT\CAMSYS\A13_03_PRECRUSH.afg
 Time: 7/16/2015, 12:05, duration 11 min 54 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 23048565, CCD-Z = 285691
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		17.8	100.0	0.799	0.893	0.744	902
#20	#16	14.3	82.2	0.806	0.891	0.720	1873
#30	#20	8.8	67.9	0.809	0.885	0.711	3212
#40	#30	6.2	59.1	0.829	0.884	0.722	6565
#50	#40	7.9	52.9	0.870	0.890	0.749	27128
#60	#50	7.1	45.0	0.897	0.899	0.749	49952
#70	#60	5.2	37.9	0.900	0.901	0.732	56648
#140	#70	13.2	32.7	0.903	0.903	0.741	776010
PAN	#140	19.5	19.5	0.894	0.923	0.734	50866912



Characteristics

Q3 [%]	x [μm]
10.0	83.8
50.0	360.6
90.0	1377.6
SPAN3 =	3.588
U3 =	7.491
Mv3(x) =	590.1 μm
Sigma3(x) =	506.1 μm

Mean value SPHT3 = 0.849
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.722
 Mean value RDNS_C3 = 0.438
 Mean value SPHT_K3 = 0.650

User