


A13-2-Crush 5k

Company: Retsch Technology
 User:
 Result file: C:\...ZER-XT-6-0-0-1005\CamsizerXT\CAMDAT\A13-2-Crush 5k\A13-2-Crush 5k_2014-06-10_022.rdf
 Task file: C:\CAMSIZER-XT-6-0-0-1005\CamsizerXT\CAMSYS\A13-2-Crush 5k.afg
 Time: 06/10/14 , 14:11 , duration 20 min 8 s at 0.4 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 51144728 , CCD-Z = 532182
 Velocity adaption: X-Fall-Sand-1micron-3mm.ftv
 Fitting: no

Material:

ASTM(+)	No(-)	p3 [%]
> #16		0.00
#20	#16	0.00
#30	#20	0.00
#40	#30	0.72
#50	#40	21.67
#60	#50	30.77
#70	#60	24.00
#140	#70	18.59
PAN	#140	4.25



Characteristics

Q3 [%]	x [μm]
10.0	165.20
50.0	254.40
90.0	336.27
Mv3(x) =	251.80 μm
Sigma3(x) =	71.26 μm

User