


A16_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A16_02_PRECRUSH\A16_02_PRECRUSH308.rdf
 Task file: C:\CamsizerXT\CAMSYS\A16_02_PRECRUSH.afg
 Time: 7/16/2015 , 10:25 , duration 10 min 49 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 9496592 , CCD-Z = 121431
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		8.8	100.0	0.787	0.903	0.751	297
#20	#16	3.7	91.2	0.792	0.897	0.755	511
#30	#20	3.3	87.5	0.795	0.883	0.748	1321
#40	#30	5.5	84.2	0.804	0.874	0.749	6390
#50	#40	8.7	78.7	0.832	0.872	0.743	28963
#60	#50	7.2	70.0	0.862	0.879	0.742	49663
#70	#60	8.2	62.8	0.882	0.885	0.741	92940
#140	#70	37.9	54.6	0.891	0.896	0.732	1801706
PAN	#140	16.7	16.7	0.883	0.925	0.722	20660849



Characteristics

Q3 [%]	x [μm]
10.0	92.2
50.0	195.5
90.0	1071.1
SPAN3 =	5.007
U3 =	2.555
Mv3(x) =	386.0 μm
Sigma3(x) =	496.2 μm

Mean value SPHT3 = 0.857
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.723
 Mean value RDNS_C3 = 0.487
 Mean value SPHT_K3 = 0.654

User