


A16_03_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A16_03_6K\A16_03_6K045.rdf
 Task file: C:\CamsizerXT\CAMSYS\A16_03_6K.afg
 Time: 7/30/2015, 14:13, duration 44 min 34 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 85786015, CCD-Z = 1021113
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.942	0.962	0.825	1
#40	#30	0.0	100.0	0.844	0.891	0.693	9
#50	#40	0.0	100.0	0.791	0.845	0.749	75
#60	#50	0.4	100.0	0.877	0.879	0.782	1860
#70	#60	4.4	99.6	0.915	0.901	0.781	32833
#140	#70	62.9	95.2	0.916	0.907	0.758	2054176
PAN	#140	32.3	32.3	0.890	0.913	0.726	201260836



Characteristics

Q3 [%]	x [μm]
10.0	53.1
50.0	123.5
90.0	193.5
SPAN3 = 1.136	
U3 = 2.514	
Mv3(x) = 124.9 μm	
Sigma3(x) = 50.7 μm	

Mean value SPHT3 = 0.902
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.734
 Mean value RDNS_C3 = 0.638
 Mean value SPHT_K3 = 0.670

User