


A16_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A16_03_PRECRUSH\A16_03_PRECRUSH324.rdf
 Task file: C:\CamsizerXT\CAMSYS\A16_03_PRECRUSH.afg
 Time: 7/16/2015, 13:54, duration 15 min 11 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 24235405, CCD-Z = 269303
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.426	0.839	0.320	2
#20	#16	1.2	99.9	0.766	0.879	0.767	196
#30	#20	5.3	98.7	0.797	0.881	0.754	1895
#40	#30	8.4	93.4	0.821	0.880	0.755	8510
#50	#40	12.3	85.0	0.849	0.882	0.755	35596
#60	#50	8.3	72.7	0.872	0.886	0.750	50101
#70	#60	7.9	64.4	0.884	0.888	0.745	77764
#140	#70	34.2	56.5	0.896	0.898	0.741	1479381
PAN	#140	22.3	22.3	0.899	0.925	0.756	42971167



Characteristics

Q3 [%]	x [μm]
10.0	74.7
50.0	184.3
90.0	515.3
SPAN3 =	2.390
U3 =	3.049
Mv3(x) =	244.9 μm
Sigma3(x) =	188.9 μm

Mean value SPHT3 = 0.870
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.736
 Mean value RDNS_C3 = 0.517
 Mean value SPHT_K3 = 0.689

User