


A16_06_6K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\A16_06_6K\A16_06_6K100.rdf
Task file:	C:\CamsizerXT\CAMSYS\A16_06_6K.afg
Time:	7/27/2015 , 15:19 , duration 44 min 57 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 168024477 , CCD-Z = 97
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.1	100.0	0.707	0.885	0.578	9
#40	#30	0.0	99.9	0.802	0.875	0.708	27
#50	#40	0.3	99.9	0.795	0.856	0.721	338
#60	#50	1.1	99.6	0.873	0.878	0.773	3540
#70	#60	9.1	98.5	0.911	0.899	0.778	44362
#140	#70	72.8	89.4	0.922	0.900	0.755	1334511
PAN	#140	16.6	16.6	0.931	0.900	0.746	231896



Mean value SPHT3 = 0.915
Mean value Symm3 = 0.898
Mean value b/l3 = 0.744
Mean value RDNS_C3 = 0.300
Mean value SPHT_K3 = 0.700

User