


A16_06_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A16_06_PRECRUSH\A16_06_PRECRUSH301.rdf
 Task file: C:\CamsizerXT\CAMSYS\A16_06_PRECRUSH.afg
 Time: 7/15/2015 , 16:06 , duration 17 min 56 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 32332809 , CCD-Z = 418200
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.4	100.0	0.761	0.883	0.713	17
#20	#16	3.7	99.6	0.784	0.888	0.754	440
#30	#20	7.6	95.9	0.797	0.883	0.740	2099
#40	#30	6.8	88.3	0.812	0.879	0.742	5427
#50	#40	7.6	81.5	0.831	0.877	0.743	17880
#60	#50	5.3	73.9	0.855	0.879	0.748	26734
#70	#60	6.6	68.6	0.881	0.886	0.752	55269
#140	#70	36.9	62.0	0.890	0.894	0.736	1326891
PAN	#140	25.1	25.1	0.894	0.919	0.737	56750965



Characteristics

Q3 [%]	x [μm]
10.0	76.1
50.0	165.9
90.0	650.6
SPAN3 = 3.464	
U3 = 2.670	
Mv3(x) = 261.4 μm	
Sigma3(x) = 240.6 μm	

Mean value SPHT3 = 0.863
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.499
 Mean value SPHT_K3 = 0.664

User