


A17_02_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A17_02_5K\A17_02_5K048.rdf
 Task file: C:\CamsizerXT\CAMSYS\A17_02_5K.afg
 Time: 7/31/2015, 11:11, duration 26 min 56 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 39281017, CCD-Z = 235650
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.875	0.894	0.779	1
#40	#30	0.0	100.0	0.681	0.852	0.708	4
#50	#40	0.0	100.0	0.719	0.772	0.742	86
#60	#50	0.6	100.0	0.890	0.880	0.787	6218
#70	#60	6.6	99.4	0.925	0.904	0.782	105699
#140	#70	79.3	92.8	0.908	0.905	0.744	4647957
PAN	#140	13.5	13.5	0.840	0.897	0.668	82371692



Characteristics

Q3 [%]	x [μm]
10.0	99.0
50.0	145.6
90.0	204.6
SPAN3 = 0.726	
U3 = 1.603	
Mv3(x) = 148.3 μm	
Sigma3(x) = 43.1 μm	

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.722
 Mean value RDNS_C3 = 0.511
 Mean value SPHT_K3 = 0.644

User