


A17_02_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A17_02_6K\A17_02_6K046.rdf
 Task file: C:\CamsizerXT\CAMSYS\A17_02_6K.afg
 Time: 7/31/2015, 9:51, duration 30 min 20 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 63733722, CCD-Z = 555943
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.930	0.923	0.757	3
#50	#40	0.0	100.0	0.716	0.782	0.716	66
#60	#50	0.6	100.0	0.897	0.886	0.789	5325
#70	#60	7.0	99.4	0.928	0.907	0.784	93176
#140	#70	74.4	92.4	0.915	0.908	0.747	3559991
PAN	#140	18.0	18.0	0.860	0.904	0.688	158406244



Characteristics

Q3 [%]	x [μm]
10.0	86.0
50.0	144.7
90.0	206.1
SPAN3 = 0.830	
U3 = 1.846	
Mv3(x) = 145.4 μm	
Sigma3(x) = 47.5 μm	

Mean value SPHT3 = 0.900
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.724
 Mean value RDNS_C3 = 0.581
 Mean value SPHT_K3 = 0.646

User