


A17_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A17_03_PRECRUSH\A17_03_PRECRUSH064.rdf
 Task file: C:\CamsizerXT\CAMSYS\A17_03_PRECRUSH.afg
 Time: 7/16/2015 , 18:22 , duration 11 min 44 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 727098 , CCD-Z = 8742
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		2.2	100.0	0.661	0.870	0.595	8
#20	#16	1.5	97.8	0.762	0.882	0.766	28
#30	#20	1.8	96.3	0.777	0.877	0.760	89
#40	#30	5.6	94.5	0.802	0.865	0.752	820
#50	#40	15.9	88.9	0.868	0.883	0.753	6510
#60	#50	15.3	73.0	0.894	0.893	0.748	12364
#70	#60	14.0	57.7	0.902	0.897	0.735	18383
#140	#70	33.3	43.7	0.895	0.898	0.722	167622
PAN	#140	10.4	10.4	0.851	0.913	0.681	1365229



Mean value SPHT3 = 0.868
 Mean value Symm3 = 0.892
 Mean value b/l3 = 0.717
 Mean value RDNS_C3 = 0.508
 Mean value SPHT_K3 = 0.640

User