


A17\_04\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDATA\A17\_04\_PRECRUSH\A17\_04\_PRECRUSH303.rdf  
 Task file: C:\CamsizerXT\CAMSYS\A17\_04\_PRECRUSH.afg  
 Time: 7/15/2015, 16:39, duration 14 min 14 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 6590823, CCD-Z = 96537  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.2	100.0	0.733	0.872	0.759	29
#30	#20	1.0	99.8	0.773	0.872	0.751	421
#40	#30	2.7	98.8	0.794	0.865	0.745	3272
#50	#40	8.2	96.1	0.851	0.874	0.753	28553
#60	#50	9.8	87.9	0.883	0.886	0.747	66624
#70	#60	12.4	78.1	0.899	0.893	0.745	136552
#140	#70	55.5	65.7	0.902	0.903	0.735	2328828
PAN	#140	10.2	10.2	0.879	0.925	0.708	12409544



Mean value SPHT3 = 0.883  
 Mean value Symm3 = 0.897  
 Mean value b/l3 = 0.721  
 Mean value RDNS\_C3 = 0.580  
 Mean value SPHT\_K3 = 0.644

User