


A17_05_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A17_05_5K\A17_05_5K049.rdf
 Task file: C:\CamsizerXT\CAMSYS\A17_05_5K.afg
 Time: 8/1/2015, 14:03, duration 30 min 35 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 43881072, CCD-Z = 214157
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.775	0.816	0.747	36
#60	#50	0.3	100.0	0.881	0.879	0.788	1648
#70	#60	2.8	99.7	0.913	0.897	0.783	30215
#140	#70	74.8	96.9	0.907	0.903	0.751	3423638
PAN	#140	22.1	22.1	0.853	0.899	0.680	61955425



Characteristics

Q3 [%]	x [μm]
10.0	87.4
50.0	128.7
90.0	185.8
SPAN3 = 0.764	
U3 = 1.573	
Mv3(x) = 132.3 μm	
Sigma3(x) = 40.2 μm	

Mean value SPHT3 = 0.890
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.723
 Mean value RDNS_C3 = 0.495
 Mean value SPHT_K3 = 0.647

User