


A17_05_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A17_05_6K\A17_05_6K055.rdf
 Task file: C:\CamsizerXT\CAMSYS\A17_05_6K.afg
 Time: 8/1/2015, 11:42, duration 36 min 37 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 47939856, CCD-Z = 304009
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.800	0.831	0.718	34
#60	#50	0.2	100.0	0.876	0.875	0.782	1032
#70	#60	2.2	99.8	0.914	0.897	0.786	18493
#140	#70	71.0	97.6	0.909	0.904	0.754	2676725
PAN	#140	26.6	26.6	0.860	0.902	0.686	92110975



Characteristics

Q3 [%]	x [μm]
10.0	77.0
50.0	125.6
90.0	180.1
SPAN3 =	0.821
U3 =	1.735
Mv3(x) =	126.8 μm
Sigma3(x) =	41.2 μm

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.723
 Mean value RDNS_C3 = 0.517
 Mean value SPHT_K3 = 0.645

User