


A19_01_5K

Company:
User:
Result file: C:\CamsizerXT\CAMDAT\A19_01_5K\A19_01_5K321.rdf
Task file: C:\CamsizerXT\CAMSYS\A19_01_5K.afg
Time: 8/2/2015 , 10:02 , duration 48 min 27 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
No. of particles: CCD-B = 134359392 , CCD-Z = 417017
Velocity adaption: no
Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.576	0.842	0.660	3
#30	#20	0.1	100.0	0.649	0.842	0.645	24
#40	#30	0.1	99.9	0.745	0.850	0.700	91
#50	#40	0.2	99.8	0.790	0.847	0.720	836
#60	#50	0.6	99.6	0.851	0.866	0.755	4021
#70	#60	3.6	99.0	0.905	0.894	0.779	39656
#140	#70	66.6	95.4	0.909	0.906	0.764	3172893
PAN	#140	28.8	28.8	0.853	0.894	0.714	150918619



Characteristics

Q3 [%]	x [μm]
10.0	55.0
50.0	127.8
90.0	190.3
SPAN3 =	1.060
U3 =	2.492
Mv3(x) =	128.0 μm
Sigma3(x) =	54.5 μm

Mean value SPHT3 = 0.888
Mean value Symm3 = 0.901
Mean value b/l3 = 0.738
Mean value RDNS_C3 = 0.457
Mean value SPHT_K3 = 0.687

User