


A20_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A20_01_PRECRUSH\A20_01_PRECRUSH255.rdf
 Task file: C:\CamsizerXT\CAMSYS\A20_01_PRECRUSH.afg
 Time: 7/14/2015, 10:34, duration 8 min 14 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 17759771, CCD-Z = 154763
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.1	100.0	0.756	0.826	0.751	66
#40	#30	4.2	99.9	0.842	0.859	0.756	9039
#50	#40	38.0	95.7	0.907	0.899	0.760	208170
#60	#50	33.8	57.7	0.917	0.910	0.738	341776
#70	#60	16.4	23.9	0.910	0.911	0.705	243760
#140	#70	6.7	7.5	0.890	0.905	0.674	232068
PAN	#140	0.8	0.8	0.855	0.908	0.718	24658988



Mean value SPHT3 = 0.900
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.722
 Mean value RDNS_C3 = 0.662
 Mean value SPHT_K3 = 0.641

User