


A21_01_PRECRUSH

Company:
User:
Result file: C:\CamsizerXT\CAMDAT\A21_01_PRECRUSH\A21_01_PRECRUSH280.rdf
Task file: C:\CamsizerXT\CAMSYS\A21_01_PRECRUSH.afg
Time: 7/14/2015 , 16:38 , duration 12 min 6 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
No. of particles: CCD-B = 5561638 , CCD-Z = 99468
Velocity adaption: no
Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.851	0.893	0.725	6
#30	#20	0.1	100.0	0.824	0.884	0.739	44
#40	#30	1.8	99.9	0.800	0.850	0.753	3602
#50	#40	14.1	98.1	0.856	0.867	0.748	72295
#60	#50	24.5	84.0	0.901	0.893	0.750	240647
#70	#60	28.2	59.5	0.914	0.904	0.736	428741
#140	#70	30.9	31.3	0.907	0.908	0.705	982715
PAN	#140	0.4	0.4	0.840	0.907	0.664	18961428



Characteristics

Q3 [%]	x [μm]
10.0	174.6
50.0	237.1
90.0	326.7
SPAN3 = 0.642	
U3 = 1.436	
Mv3(x) = 245.8 μm	
Sigma3(x) = 66.2 μm	

Mean value SPHT3 = 0.891
Mean value Symm3 = 0.894
Mean value b/l3 = 0.715
Mean value RDNS_C3 = 0.533
Mean value SPHT_K3 = 0.631

User