


A21_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A21_02_PRECRUSH\A21_02_PRECRUSH312.rdf
 Task file: C:\CamsizerXT\CAMSYS\A21_02_PRECRUSH.afg
 Time: 7/16/2015 , 11:06 , duration 9 min 11 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 10732294 , CCD-Z = 146354
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.817	0.876	0.660	4
#30	#20	0.1	100.0	0.763	0.868	0.647	19
#40	#30	1.8	99.9	0.783	0.843	0.752	3827
#50	#40	11.6	98.1	0.827	0.854	0.735	54338
#60	#50	15.1	86.5	0.876	0.877	0.737	143382
#70	#60	22.0	71.4	0.904	0.895	0.740	330943
#140	#70	48.1	49.4	0.908	0.906	0.717	1709215
PAN	#140	1.3	1.3	0.853	0.915	0.684	28649929



Characteristics

Q3 [%]	x [μm]
10.0	153.7
50.0	212.8
90.0	320.8
SPAN3 =	0.785
U3 =	1.483
Mv3(x) =	226.7 μm
Sigma3(x) =	72.1 μm

Mean value SPHT3 = 0.882
 Mean value Symm3 = 0.890
 Mean value b/l3 = 0.711
 Mean value RDNS_C3 = 0.499
 Mean value SPHT_K3 = 0.623

User