


A23\_01\_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDATA\A23_01_PRECRUSH\A23_01_PRECRUSH286.rdf
Task file:	C:\CamsizerXT\CAMSYS\A23_01_PRECRUSH.afg
Time:	7/15/2015 , 11:30 , duration 14 min 55 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 69676236 , CCD-Z = 578614
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.3	100.0	0.839	0.895	0.735	86
#40	#30	7.9	99.7	0.848	0.887	0.762	7745
#50	#40	15.8	91.8	0.861	0.887	0.746	35968
#60	#50	9.0	76.0	0.877	0.887	0.745	44812
#70	#60	8.0	67.0	0.891	0.891	0.743	64227
#140	#70	39.4	59.0	0.901	0.901	0.736	1152232
PAN	#140	19.6	19.6	0.878	0.905	0.728	93398652



Mean value SPHT3 = 0.878
Mean value Symm3 = 0.896
Mean value b/l3 = 0.726
Mean value RDNS_C3 = 0.489
Mean value SPHT_K3 = 0.662

User