


A24_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A24_01_PRECRUSH\A24_01_PRECRUSH188.rdf
 Task file: C:\CamsizerXT\CAMSYS\A24_01_PRECRUSH.afg
 Time: 7/7/2015 , 9:48 , duration 9 min 55 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 6208834 , CCD-Z = 97693
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.9	100.0	0.732	0.888	0.745	124
#20	#16	2.6	98.1	0.738	0.877	0.727	463
#30	#20	4.1	95.5	0.765	0.870	0.734	2060
#40	#30	5.9	91.4	0.793	0.867	0.737	8296
#50	#40	8.9	85.5	0.818	0.860	0.731	35810
#60	#50	6.8	76.6	0.846	0.862	0.730	56164
#70	#60	9.0	69.8	0.878	0.876	0.734	125236
#140	#70	57.5	60.8	0.905	0.907	0.732	2628088
PAN	#140	3.3	3.3	0.879	0.929	0.701	16888586



Characteristics

Q3 [%]	x [μm]
10.0	126.1
50.0	186.9
90.0	549.2
SPAN3 =	2.263
U3 =	1.663
Mv3(x) =	277.4 μm
Sigma3(x) =	246.2 μm

Mean value SPHT3 = 0.864
 Mean value Symm3 = 0.891
 Mean value b/l3 = 0.717
 Mean value RDNS_C3 = 0.445
 Mean value SPHT_K3 = 0.642

User