


A24_02_5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A24_02_5K\A24_02_5K089.rdf
 Task file: C:\CamsizerXT\CAMSYS\A24_02_5K.afg
 Time: 7/23/2015 , 13:04 , duration 33 min 29 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 47158720 , CCD-Z = 23557
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.567	0.824	0.656	3
#50	#40	0.1	100.0	0.767	0.837	0.738	131
#60	#50	0.2	99.9	0.783	0.834	0.740	1002
#70	#60	1.2	99.7	0.850	0.863	0.761	9106
#140	#70	65.4	98.5	0.884	0.896	0.757	2548102
PAN	#140	33.1	33.1	0.841	0.900	0.692	25441694



Characteristics

Q3 [%]	x [μm]
10.0	79.6
50.0	116.2
90.0	156.6
SPAN3 = 0.663	
U3 = 1.535	
Mv3(x) = 117.2 μm	
Sigma3(x) = 34.9 μm	

Mean value SPHT3 = 0.866
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.413
 Mean value SPHT_K3 = 0.664

User