


A24_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A24_02_PRECRUSH\A24_02_PRECRUSH259.rdf
 Task file: C:\CamsizerXT\CAMSYS\A24_02_PRECRUSH.afg
 Time: 7/14/2015, 11:14, duration 13 min 49 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 24387179, CCD-Z = 394105
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		7.1	100.0	0.796	0.898	0.750	243
#20	#16	5.8	92.9	0.785	0.895	0.702	519
#30	#20	4.1	87.1	0.793	0.888	0.717	1061
#40	#30	3.6	83.0	0.814	0.884	0.735	2740
#50	#40	3.9	79.4	0.837	0.882	0.743	8704
#60	#50	2.3	75.5	0.850	0.877	0.744	11303
#70	#60	2.4	73.2	0.860	0.875	0.743	20448
#140	#70	37.7	70.8	0.896	0.897	0.749	1803428
PAN	#140	33.1	33.1	0.906	0.929	0.742	52356455



Characteristics

Q3 [%]	x [μm]
10.0	79.9
50.0	123.9
90.0	1021.6
SPAN3 = 7.602	
U3 = 1.782	
Mv3(x) = 314.3 μm	
Sigma3(x) = 400.1 μm	

Mean value SPHT3 = 0.870
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.570
 Mean value SPHT_K3 = 0.658

User