


A26_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A26_01_PRECRUSH\A26_01_PRECRUSH252.rdf
 Task file: C:\CamsizerXT\CAMSYS\A26_01_PRECRUSH.afg
 Time: 7/13/2015 , 15:58 , duration 19 min 51 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 72785356 , CCD-Z = 422824
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.1	100.0	0.879	0.907	0.825	9
#30	#20	0.4	99.9	0.845	0.899	0.750	86
#40	#30	3.0	99.5	0.867	0.902	0.763	1964
#50	#40	4.8	96.5	0.875	0.901	0.756	7501
#60	#50	2.3	91.7	0.881	0.897	0.755	7863
#70	#60	2.1	89.4	0.886	0.895	0.757	11919
#140	#70	18.3	87.3	0.886	0.891	0.749	523194
PAN	#140	69.0	69.0	0.887	0.914	0.739	131979561



Characteristics

Q3 [%]	x [μm]
10.0	46.9
50.0	82.5
90.0	262.7
SPAN3 = 2.614	
U3 = 1.970	
Mv3(x) = 119.6 μm	
Sigma3(x) = 108.9 μm	

Mean value SPHT3 = 0.881
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.730
 Mean value RDNS_C3 = 0.555
 Mean value SPHT_K3 = 0.663

User