


A27_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A27_01_PRECRUSH\A27_01_PRECRUSH177.rdf
 Task file: C:\CamsizerXT\CAMSYS\A27_01_PRECRUSH.afg
 Time: 6/24/2015 , 16:34 , duration 9 min 24 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 22387414 , CCD-Z = 183514
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.816	0.860	0.684	6
#30	#20	0.3	100.0	0.786	0.833	0.757	142
#40	#30	13.4	99.7	0.835	0.863	0.746	19029
#50	#40	39.2	86.3	0.885	0.893	0.739	133643
#60	#50	19.9	47.1	0.903	0.905	0.729	136472
#70	#60	11.5	27.2	0.907	0.907	0.721	127065
#140	#70	13.1	15.7	0.898	0.905	0.710	412071
PAN	#140	2.6	2.6	0.854	0.906	0.711	58088116



Characteristics

Q3 [%]	x [μm]
10.0	183.9
50.0	307.1
90.0	446.7
SPAN3 =	0.856
U3 =	1.804
Mv3(x) =	310.3 μm
Sigma3(x) =	103.4 μm

Mean value SPHT3 = 0.878
 Mean value Symm3 = 0.893
 Mean value b/l3 = 0.716
 Mean value RDNS_C3 = 0.528
 Mean value SPHT_K3 = 0.638

User