


A28-2-Crush 6k

Company: Retsch Technology
 User:
 Result file: C:\...ZER-XT-6-0-0-1005\CamsizerXT\CAMDAT\A28-2-Crush 6k\A28-2-Crush 6k_2014-06-05_007.rdf
 Task file: C:\CAMSIZER-XT-6-0-0-1005\CamsizerXT\CAMSYS\A28-2-Crush 6k.afg
 Time: 06/05/14 , 9:55 , duration 29 min 42 s at 0.4 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 53146961 , CCD-Z = 949324
 Velocity adaption: X-Fall-Sand-1micron-3mm.ftv
 Fitting: no

Material:

ASTM(+)	No(-)	p3 [%]
> #16		0.00
#20	#16	0.00
#30	#20	0.00
#40	#30	0.00
#50	#40	0.00
#60	#50	0.09
#70	#60	1.39
#140	#70	81.72
PAN	#140	16.80

**Characteristics**

Q3 [%]	x [μm]
10.0	94.70
50.0	130.21
90.0	172.54
Mv3(x) =	131.13 μm
Sigma3(x) =	34.19 μm

User