


A28_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A28_01_PRECRUSH\A28_01_PRECRUSH261.rdf
 Task file: C:\CamsizerXT\CAMSYS\A28_01_PRECRUSH.afg
 Time: 7/14/2015 , 11:40 , duration 14 min 35 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 8959678 , CCD-Z = 157297
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.1	100.0	0.829	0.906	0.761	9
#30	#20	0.5	99.9	0.840	0.905	0.794	155
#40	#30	1.9	99.4	0.841	0.891	0.782	1797
#50	#40	3.2	97.5	0.845	0.880	0.758	8176
#60	#50	2.9	94.3	0.855	0.873	0.753	14712
#70	#60	3.9	91.4	0.866	0.872	0.750	33643
#140	#70	66.1	87.5	0.904	0.905	0.746	2843125
PAN	#140	21.4	21.4	0.900	0.934	0.728	19587821



Characteristics

Q3 [%]	x [μm]
10.0	91.8
50.0	129.6
90.0	233.6
SPAN3 =	1.094
U3 =	1.514
Mv3(x) =	153.5 μm
Sigma3(x) =	87.7 μm

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.656
 Mean value SPHT_K3 = 0.654

User