


A28_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A28_02_PRECRUSH\A28_02_PRECRUSH288.rdf
 Task file: C:\CamsizerXT\CAMSYS\A28_02_PRECRUSH.afg
 Time: 7/15/2015, 12:44, duration 10 min 58 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 7226809, CCD-Z = 112445
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.3	100.0	0.760	0.897	0.700	40
#20	#16	1.6	98.7	0.775	0.886	0.739	153
#30	#20	2.5	97.1	0.789	0.885	0.742	684
#40	#30	5.0	94.6	0.814	0.880	0.752	3843
#50	#40	7.5	89.6	0.832	0.873	0.748	16544
#60	#50	5.6	82.1	0.846	0.869	0.743	25888
#70	#60	5.8	76.5	0.859	0.868	0.737	42839
#140	#70	61.7	70.7	0.905	0.905	0.741	2175814
PAN	#140	9.0	9.0	0.886	0.927	0.701	15676492



Characteristics

Q3 [%] x [μm]
 10.0 107.4
 50.0 148.7
 90.0 434.6
 SPAN3 = 2.201
 U3 = 1.564
 Mv3(x) = 228.7 μm
 Sigma3(x) = 216.2 μm

Mean value SPHT3 = 0.875
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.524
 Mean value SPHT_K3 = 0.657

User