


A29-2-Crush 6k

Company: Retsch Technology
 User:
 Result file: C:\...ZER-XT-6-0-0-1005\CamsizerXT\CAMDAT\A29-2-Crush 6k\A29-2-Crush 6k_2014-06-05_006.rdf
 Task file: C:\CAMSIZER-XT-6-0-0-1005\CamsizerXT\CAMSYS\A29-2-Crush 6k.afg
 Time: 06/05/14 , 9:28 , duration 23 min 1 s at 0.4 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 15437893 , CCD-Z = 625583
 Velocity adaption: X-Fall-Sand-1micron-3mm.ftv
 Fitting: no

Material:

ASTM(+)	No(-)	p3 [%]
> #16		0.00
#20	#16	0.00
#30	#20	0.00
#40	#30	0.00
#50	#40	0.03
#60	#50	1.16
#70	#60	11.98
#140	#70	80.20
PAN	#140	6.63

**Characteristics**

Q3 [%]	x [μm]
10.0	114.97
50.0	167.86
90.0	217.68
Mv3(x) =	166.37 μm
Sigma3(x) =	40.64 μm

User