


A29_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A29_01_PRECRUSH\A29_01_PRECRUSH265.rdf
 Task file: C:\CamsizerXT\CAMSYS\A29_01_PRECRUSH.afg
 Time: 7/14/2015, 12:25, duration 12 min 38 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 9171363, CCD-Z = 110496
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.603	0.749	0.767	7
#40	#30	3.8	100.0	0.808	0.860	0.761	7524
#50	#40	13.9	96.2	0.840	0.864	0.741	63479
#60	#50	15.4	82.3	0.890	0.886	0.754	151175
#70	#60	23.5	66.9	0.918	0.904	0.757	366479
#140	#70	41.8	43.4	0.914	0.910	0.729	1635509
PAN	#140	1.6	1.6	0.862	0.920	0.700	15837401



Characteristics

Q3 [%]	x [μm]
10.0	150.3
50.0	221.5
90.0	353.7
SPAN3 =	0.918
U3 =	1.577
Mv3(x) =	236.6 μm
Sigma3(x) =	81.4 μm

Mean value SPHT3 = 0.890
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.503
 Mean value SPHT_K3 = 0.664

User