


A29_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A29_03_PRECRUSH\A29_03_PRECRUSH179.rdf
 Task file: C:\CamsizerXT\CAMSYS\A29_03_PRECRUSH.afg
 Time: 6/25/2015 , 13:44 , duration 9 min 18 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3632162 , CCD-Z = 55070
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.0	100.0	0.739	0.890	0.762	19
#20	#16	2.3	99.0	0.758	0.875	0.734	128
#30	#20	6.2	96.7	0.786	0.866	0.734	898
#40	#30	8.7	90.5	0.837	0.873	0.740	3621
#50	#40	19.7	81.8	0.899	0.897	0.752	24499
#60	#50	17.2	62.1	0.911	0.904	0.743	42747
#70	#60	16.9	44.9	0.918	0.908	0.741	68708
#140	#70	26.0	28.0	0.912	0.909	0.719	252678
PAN	#140	2.0	2.0	0.842	0.909	0.688	16143463



Characteristics

Q3 [%]	x [μm]
10.0	168.0
50.0	263.3
90.0	584.6
SPAN3 = 1.582	
U3 = 1.743	
Mv3(x) = 327.7 μm	
Sigma3(x) = 216.6 μm	

Mean value SPHT3 = 0.884
 Mean value Symm3 = 0.898
 Mean value b/l3 = 0.722
 Mean value RDNS_C3 = 0.522
 Mean value SPHT_K3 = 0.649

User