


A3-2 Crush 6k

Company:	Retsch Technology
User:	Alec-Alicia
Result file:	C:\Camsizer-XT-6-0-3\CAMDAT\A3-2 Crush 6k\A3-2 Crush 6k_xc_min_2014-07-17_014.rdf
Task file:	C:\Camsizer-XT-6-0-3\CAMSYS\A3-2 Crush 6k.afg
Time:	7/17/2014 , 10:04 , duration 24 min 50 s at 0.4 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 99042835 , CCD-Z = 850664
Velocity adaption:	X-Fall-Sand-1-3000microns.ftv
Fitting:	C:\Camsizer-XT-6-0-3\CAMSYS\20-40-2nd-Sieve-30-35.fte
Material:	Frac-Sand

ASTM(+)	No(-)	p3 [%]	B/L_rec3	PDN	Q0(B/Lrec) 0.9000	Q3(SPHT) 0.9000
> #16		0.00		0		
#20	#16	0.00		0		
#30	#20	0.00		0		
#40	#30	0.44	0.836	1306	76.76	54.73
#50	#40	53.65	0.799	470369	88.33	50.46
#60	#50	25.75	0.745	383850	93.87	62.58
#70	#60	5.97	0.731	143977	94.60	72.07
#140	#70	8.76	0.718	649658	94.93	77.52
PAN	#140	5.43	0.678	192723247	83.67	85.75



Q3 (b/l=0.9) = 97.5 %
 Q3 (B/L_rec=0.9) = 91.5 %

User _____