


A31_01_7K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A31_01_7K\A31_01_7K328.rdf
 Task file: C:\CamsizerXT\CAMSYS\A31_01_7K.afg
 Time: 8/3/2015, 9:39, duration 21 min 10 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 57080429, CCD-Z = 796329
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.666	0.721	0.725	169
#50	#40	27.3	100.0	0.916	0.904	0.780	282323
#60	#50	46.3	72.7	0.914	0.909	0.738	709221
#70	#60	14.7	26.4	0.900	0.907	0.694	328970
#140	#70	8.0	11.7	0.880	0.894	0.688	583539
PAN	#140	3.7	3.7	0.842	0.899	0.674	151216349



Characteristics

Q3 [%]	x [μm]
10.0	201.4
50.0	277.5
90.0	323.9
SPAN3 = 0.442	
U3 = 1.426	
Mv3(x) = 266.5 μm	
Sigma3(x) = 60.3 μm	

Mean value SPHT3 = 0.902
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.723
 Mean value RDNS_C3 = 0.636
 Mean value SPHT_K3 = 0.643

User