


A31_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A31_02_PRECRUSH\A31_02_PRECRUSH253.rdf
 Task file: C:\CamsizerXT\CAMSYS\A31_02_PRECRUSH.afg
 Time: 7/14/2015, 10:17, duration 8 min 35 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3516983, CCD-Z = 52641
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.739	0.899	0.808	2
#20	#16	0.1	100.0	0.642	0.838	0.688	13
#30	#20	0.1	99.9	0.725	0.838	0.748	99
#40	#30	0.9	99.8	0.796	0.840	0.746	1769
#50	#40	13.6	98.9	0.880	0.880	0.760	75669
#60	#50	30.9	85.3	0.907	0.898	0.755	320490
#70	#60	33.2	54.4	0.910	0.905	0.726	509195
#140	#70	20.6	21.2	0.889	0.903	0.673	586935
PAN	#140	0.6	0.6	0.814	0.903	0.655	7462065



Characteristics

Q3 [%]	x [μm]
10.0	192.8
50.0	244.9
90.0	315.7
SPAN3 =	0.502
U3 =	1.331
Mv3(x) =	251.5 μm
Sigma3(x) =	61.1 μm

Mean value SPHT3 = 0.892
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.713
 Mean value RDNS_C3 = 0.543
 Mean value SPHT_K3 = 0.623

User